



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

May 12, 2016

Mr. Tom Merker
SPRINGS WINDOW FASHIONS, LLC
7549 Graber Road
Middleton, WI 53562-1096

Reference: Laboratory Test Report
Lab Identification No. 19853
Invoice No. 50770 (Attached)

Dear Mr. Merker:

One (1) sample, identified as **HORIZONTAL ALUMINUM SLAT – 1" - PERFORATED ALABASTER/112**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame</u> <u>(seconds)</u>	<u>Weight Loss</u> <u>(percent)</u>
1	0.0	1.30
2	0.0	2.04
3	0.0	2.23
4	0.0	1.47
5	0.0	2.80
6	0.0	1.68
7	0.0	1.50
8	0.0	2.24
9	0.0	2.61
10	<u>0.0</u>	<u>2.42</u>
AVG.	0.0	2.03

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr
Attachment