

TECHNICAL DATA

PRODUCT NAME		REFLECTIVE BRONZE 10
1	VISIBLE LIGHT TRANSMITTANCE	10
2	VISIBLE LIGHT TRANSMITTANCE TOLERANCE	11 ± 3.0
3	VISIBLE LIGHT REFLECTANCE EXTERIOR	21
4	VISIBLE LIGHT REFLECTANCE INTERIOR	56
5	SOLAR ENERGY TRANSMITTANCE	10
6	SOLAR ENERGY REFLECTANCE	31
7	SOLAR ENERGY ABSORPTION	59
8	% ULTRAVIOLET LIGHT TRANSMISSION	<1
9	TOTAL SOLAR ENERGY REJECTED	74
10	SHADING COEFFICIENT	0.31
11	SOLAR HEAT GAIN COEFFICIENT	0.26
12	LUMINOUS EFFICACY	0.32
13	EMISSIVITY	0.66
14	WINTER MEDIAN U VALUE	1.01
15	GLARE REDUCTION	89
16	NIR BLOCKING AT 1025 NM	80 ± 3.0

Note:- The performance data reported on this page was tested using ASHRAE, ASTM, BSEN 410 & AIMCAL Standards. All values as applied to 1/8 inch clear glass. Test results are representative of actual production and may vary from batch to batch.