

# RIO-CRETE™ MF

## Smooth Finish Flowable Polyurethane Concrete

### TECHNOLOGY DESCRIPTION

RIO FLOORING SYSTEMS represent the next generation of polyurethane concrete technology. These Bio-Based flooring systems utilize domestically produced soybean oil and environmentally friendly packaging.

### PRODUCT DESCRIPTION

RIO-CRETE MF is a heavy-duty seamless flooring system typically installed at 3/16” in thickness. RIO-CRETE MF is tough and withstands thermal shock, impact, abrasion and chemical exposure. RIOCRETE MF is formulated with a natural additive to be resistant to fungi growth per the industry standard ASTM G-21.

### APPLICATIONS

- Bakeries
- Pharmaceutical facilities
- Supermarkets & food prep areas
- Food & beverage facilities
- Warehousing
- Laboratories

TYPICAL PROPERTIES		
Property	Results	Test Method
Compressive Strength:	7,200 psi	ASTMC-579
Tensile Strength:	1,050 psi	ASTM C-307
Flexural Strength:	2,700 psi	ASTM C-580
Bond Strength:	100% Concrete Failure	ASTMD-4541
Impact Strength, in/lbs:	>160 in-lb	ASTM D-4226
VOC:	5 gm/l	
Resistance to Fungi Growth:	Passes, Rating of 1	ASTM G-21
Shelf Life:	6 months	

*The data shown above reflects typical results based on laboratory testing under controlled conditions at 70°F. Variations from the data shown may result. Test methods are modified where applicable.*

### CURE SCHEDULE: (77°F)

Pot Life..... 15 minutes  
 Light Foot Traffic ..... 12 hours  
 Heavy Foot Traffic ..... 24 hours  
 Fully Cured ..... 7 days

### APPLICATION TEMPERATURE

Ambient: 40-85°F , Material: 50-80°F

### BENEFITS

- Seamless, hygienic finish; no grout joints
- Impact & abrasion resistant surface suitable for heavy traffic and forklift operation
- Low odor, fast installation, fast cure
- Excellent corrosion & chemical resistance
- High temperature resistant to 250°F
- Thermal shock resistant; steam cleanable
- Resistant to moisture vapor transmission (MVT)
- Anti-slip surface, meets ADA recommendations
- Resistant to fungi growth per ASTM G-21

### GENERIC DESCRIPTION

Polyurethane Concrete

### TYPICAL APPLICATION

3/16” Trowel applied monolithic floor

### AVAILABLE COLORS

Red, Dark Red, Gray, Dark Gray, Tan, Green, Blue, Light Blue, Safety Yellow

### PACKAGING & COVERAGE

- 1/2 Gallon Part A, 1/2 Gallon Part B
- 1 MF Filler Bag
- 3 fluid oz. liquid pigment

21 SF /unit for a 3/16” finished floor

### LIMITATIONS

- RIO-CRETE MF is not color stable unless UV resistant topcoat is used.
- RIO-CRETE flooring should not be installed on wet concrete.
- Floors should be sloped to drain to prevent standing water or chemicals.
- Spills should be removed as soon as possible to prevent a slipping hazard.
- Confirm product performance in specific chemical environment prior to use.
- Prepare substrate according to “Surface Preparation” portion of this document.
- Follow detailed instructions in the “Installation Steps” portion of this document.
- Always use protective clothing consistent with OSHA regulations during use.
- Refer to Safety Data Sheet for detailed safety precautions.
- For industrial/commercial use. Installation by trained personnel only.

## INSTALLATION STEPS

### PREPARATION

**Concrete surface preparation:** Apply only to properly prepared clean, dry and sound concrete substrates that are free of all coatings, sealers, curing compounds, oils, greases or any other contaminants. New concrete should ideally be cured for a minimum of 14 days to reduce possible shrinkage cracking in the concrete. RIO-CRETE MF can be installed after 7 days or when concrete reaches a minimum 3,500 psi compressive strength, which will allow for proper surface preparation, however, early curing movement, shrinkage or cracking that may occur in the concrete will be reflected through the final RIO-CRETE flooring.

- Concrete that has been contaminated with chemicals or other foreign matter must be neutralized or removed.
- Remove any laitance or weak surface layers including broom finish surface.
- Concrete should have a minimum surface tensile strength of at least 300 PSI per ASTM D-4541.
- Surface profile shall be CSP-5 or greater meeting ICRI (International Concrete Repair Institute) standard guideline #03732 for coating concrete, producing a profile equal to 40-grit sandpaper or coarser. Prepare surface by mechanical means to achieve this desired profile.
- All concrete surface irregularities, cracks, expansion joints, control joints and terminations should be properly addressed and prepared prior to application of the flooring. Moving joints and cracks will reflect through the final installed RIO-CRETE flooring.

### MIXING & APPLICATION

**IMPORTANT** – Follow the detailed application instructions and the safety instructions listed on the product Safety Data Sheets (SDS) copies available upon request. The following installation summary is for reference only and should not be relied upon as all inclusive. RIO-CRETE systems should only be installed by trained persons experienced in polyurethane concrete flooring applications.

1. To prevent lifting or delamination, keyways (minimum 5/16" wide x 5/16" deep) must be cut at all terminations, joints, columns, doorways, and drains.
2. Clean sand and dust from prepared concrete where the floor is to be installed.
3. A cove base material can be used to install a cove and/or base as required. The cove/base can be installed before or after the installation of the RIOCRETE MF depending on the specification and or the desired result.
4. Pour ½ Gallon Part A into a 5 gallon mixing pail.
5. Add 3 fluid oz. liquid pigment to Part A and mix about 15 seconds using a ½" drill and jiffy-type mixing paddle.
6. Add ½ Gallon Part B and mix another 15 seconds.
7. Gradually add all contents of a RIOCRETE MF Filler into the liquid mixture and blend thoroughly until all particles are wetted out, normally about two minutes. **DO NOT BLEND AGGRESSIVELY OR INTRODUCE AIR.**
8. Immediately after mixing (within 3 minutes), spread the mixed RIOCRETE MF onto the floor at the desired thickness, using a cam rake or trowel. Typically 3/16".
9. Lay abutting edges within 10 minutes to ensure a clean edge. A "wet edge" installation is imperative during large placements to avoid lines and ridges in the finished floor.
10. Evenly apply to desired thickness while trying to keep cam rake lines to a minimum. Backroll across slurry with spike roller to help release trapped air and blend cam rake lines. Further roll with loop/texture roller perpendicular to cam rake lines over entire floor to even and settle slurry.
11. Use of a self-leveling cement smoothing toll will aid in the removal of rake marks.

### NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Any use or application other than recommended herein is the sole responsibility of the user. Listed physical properties are typical and should not be construed as specifications. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.